

Migaku TAKAHASHI et al.

*Amended
Sub G2*

--20.(New) A magnetic recording medium according to claim 3, wherein said metal underlayer comprises a layered structure of two or more underfilms with different lattice constants.--

IN THE ABSTRACT:

Cancel the abstract as originally filed which appears on page 57. Add new abstract as enclosed herewith on a separate sheet.

REMARKS

Claims 3-6, 9-10, 12 and 16-17 were amended to correct multiple dependency. Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "VERSION WITH MARKINGS TO SHOW CHANGES MADE".

Respectfully submitted,

YOUNG & THOMPSON

By

Thomas W. Perkins
Thomas W. Perkins
Attorney for Applicant
Customer No. 000466
Registration No. 33,027
745 South 23rd Street
Arlington, VA 22202
703/ 521-2297

December 27, 2001

"VERSION WITH MARKINGS TO SHOW CHANGE MADE"

Claims 3-6, 9-10, 12 and 16-17 have been amended as follows:

3. ~~(Amended)~~ A magnetic recording medium according ~~to either one of~~ claim 1, wherein said metal underlayer incorporates an underfilm of either one of Cr and a Cr alloy, and said Cr alloy also incorporates Mo and/or W.

4. ~~(Amended)~~ A magnetic recording medium according ~~to either one of~~ claim 1, wherein said metal underlayer incorporates an underfilm of either one of Cr and a Cr alloy, and said Cr alloy incorporates one, or two or more elements selected from a group consisting of V, Nb, Hf, Zr, Ti, Mn, Ta, Ru, Re, Os, Ir, Rh, Pd, Pt, P, B, Si, Ge, N and O.

5. ~~(Amended)~~ A magnetic recording medium according to any one of claim 1, wherein a film thickness of said metal underlayer is within a range from 3 nm to 20 nm.

6. ~~(Amended)~~ A magnetic recording medium according to ~~any one of claim 1 through claim 5,~~ ~~claim 1,~~ wherein said metal underlayer comprises a layered structure of two or more underfilms with different lattice constants.

9. ~~(Amended)~~ A magnetic recording medium according ~~to either one of~~ claim 7, wherein a film thickness of said second underfilm is within a range from 1.5 nm to 8.5 nm.

10. ~~(Amended)~~ A magnetic recording medium according to ~~any one of~~ claim 1, wherein a lattice misfit of said metal underlayer and said ferromagnetic metal layer, as determined by an equation $(y-x) / (x/2 + y/2) \cdot 100(\%)$, in which x represents a length obtained by multiplying by $\sqrt{2}$ a lattice constant of said metal underlayer and y represents a c axis length of a crystal lattice of said ferromagnetic metal layer, is a value from 0.5% to 2.5%.

12. ~~(Amended)~~ A magnetic recording medium according to ~~any one of~~ claim 1, wherein in a crystal lattice of said ferromagnetic metal layer of said cobalt based alloy, an interatomic distance a in a direction of a normal line to said ferromagnetic metal layer is larger than an interatomic distance b in a direction within a plane of said ferromagnetic metal layer.

16. ~~(Amended)~~ A method of producing a magnetic recording medium according to ~~either one of claim 14 and claim 15,~~ ~~claim 14,~~ wherein in order to control said lattice misfit, either one of a positive and a negative bias of 0 V to 300 V is applied to said base material during film fabrication of said ferromagnetic metal layer.

17. ~~(Amended)~~ A magnetic recording device comprising a magnetic recording medium according to ~~any one of~~ claim 1 ~~through claim 13~~, a drive section for driving said magnetic recording medium, and a magnetic head for carrying out recording and playback of magnetic information, wherein said

magnetic head performs recording and playback of magnetic information on a moving said magnetic recording medium.

The abstract has been amended as follows:

ABSTRACT OF THE DISCLOSURE

~~The present invention provides a~~ magnetic recording medium ~~with~~ was a high normalized coercive force and superior thermal stability, as well as a method of producing such a magnetic recording medium and a magnetic recording device incorporating such a magnetic recording medium. A magnetic recording medium according to the present invention stability.

The magnetic recording medium comprises a non-magnetic base material, and a ferromagnetic metal layer of cobalt based alloy formed on top of this base material with a metal underlayer disposed therebetween, and displays a coercive force H_c of at least 2000 (Oe) and an anisotropic magnetic field H_k^{grain} of at least 10,000 (Oe). Furthermore, magnetic recording media in which the aforementioned metal underlayer and/or the ferromagnetic metal layer are fabricated in a film fabrication chamber with an ultimate vacuum at the 10^{-9} Torr level are preferred.

~~—A preferred.~~ A magnetic recording medium according to the present invention can be ideally applied to hard disks, floppy disks, and magnetic tapes and the like.

ABSTRACT OF THE DISCLOSURE

AS
A magnetic recording medium was a high normalized coercive force and superior thermal stability. The magnetic recording medium comprises a non-magnetic base material, and a ferromagnetic metal layer of cobalt based alloy formed on top of this base material with a metal underlayer disposed therebetween, and displays a coercive force H_c of at least 2000 (Oe) and an anisotropic magnetic field H_k^{grain} of at least 10,000 (Oe). Furthermore, magnetic recording media in which the aforementioned metal underlayer and/or the ferromagnetic metal layer are fabricated in a film fabrication chamber with an ultimate vacuum at the 10^{-9} Torr level are preferred. A magnetic recording medium according to the present invention can be ideally applied to hard disks, floppy disks, and magnetic tapes and the like.

10026709-122701